



P o l y m e r s

*Rosehill Polymers Ltd. Rose Hill Mills, Beech Road, Sowerby Bridge
West Yorkshire HX6 2JT*

Telephone: (01422) 839456. Fax: (01422) 316952

TPV granules UV Resistance

Rosehill Polymers TPV Granules are tested in a QUV Weatherometer Machine, manufactured by Q-LAB. The granules are exposed to alternating cycles of UV light and condensation. They are measured on a standard Grey Scale after 1000 hours exposure.

Readings are between 1 and 5.

5 represents no change and 1 represents significant change.

A resistance of 3 minimum is required by DIN standards.

CODE	COLOUR	READING
RH01	Standard Red	5
RH02	Bright Red	5
RH10	Standard Green	5
RH11	Bright Green	4
RH20	Standard Blue	4
RH21	Purple	3/4
RH22	Light Blue	5
RH23	Azure Blue	5
RH30	Beige	5
RH31	Cream	4
RH32	Brown	4/5
RH40	Mustard Yellow	4/5
RH41	Bright Yellow	4/5
RH50	Orange	5
RH60	Dark Grey	5
RH61	Light Grey	4

N. Hope
New Developments Manager

30th November 2006.